

# PAREXDAVCO TECHNICAL SERVICES REPORT

Date Conducted: 30<sup>th</sup> April 2009 Reference: P1133

## TESTED ON BEHALF OF:

Customer: All Styles Australia

Address: Unit 1, 26 Redfern Street  
Wetherill Park NSW 2164

Contact Name: Robert

Site / Job details: (if applicable) N/A

Tile Type & Description: Blue glass mosaic 25mm x 25mm with a hot melt backing.

## TEST DETAILS:

Standard: AS4992

Tests Conducted: 28 days tensile adhesion.  
7 days / 21 days immersion tensile adhesion

Adhesives Tested: Sanitized Colorgrout #11 combined with Glass Mosaic Additive.

## RESULTS:

	<b>Tensile Strength Results (MPa)</b>	<b>Standard Requirement (MPa)</b>
28 day tensile	1.3 Mpa	≥ 0.5 MPa
7 days / 21 days at 70°C	1.1 Mpa	≥ 0.5 MPa

## RECOMMENDATIONS:

The tensile bond strengths obtained clearly indicate that Sanitized Colorgrout combined with Glass Mosaic Additive is a suitable adhesive system for these tiles.

A handwritten signature in black ink, appearing to read 'John Sury', written in a cursive style.

John Sury

**PAREXDAVCO Australia PTY LTD**

The information in this report is based solely on the information and samples made available to ParexDavco Australia at the time of writing. Compliance with the relevant standards is the responsibility of the Specifier, Installer and/or tile manufacturer. Although care has been taken to ensure the information in this document is correct no liability will be accepted for its use.